



DIMAPCHEM RR

LIQUID FOR CLEANING R-BARS AND STEEL SURFACES

BENEFITS

- Simple application by brush.
- Effective rust removal, even from areas difficult to reach.
- Contains no chloride-no chance of enhancing corrosion.
- Cost effective coverage.
- Removes oil, grease, carbon and dust particles deposited.
- Self lubricating.
- Shine and metal finishing.

PRODUCT

DIMAPCHEMRR is a specially designed organic liquid which releases parts bound fast due to rust, corrosion, carbon, tar, etc. It is used effectively to clean rust from steel surfaces before applying any protective coating on it.

AREAS OF APPLICATION

During repairs to concrete structures.

Maintenance of mild steel structures like tanks, water pipelines, shuttering plates and other corroded steel surfaces.

OTHER INFORMATION

DIMAPCHEM EP (S) Solvent High Build Protective &
Decorative Coating For Steel
Surfaces

DIMAPCHEM LP Epoxy High Solids Coating

DIMAPCHEM SF A Thixotropic Protective Coating For
Concrete And Steel Surfaces

DIMAPCHEM AC A Clear, Acrylic Polymer Sealer For Old And New Concrete

SAFECPRE VC A Solvent Free Ultra-chemical

Resistant Vinyl Ester Based Coating

For Concrete And Steel Substrates

PACKING & COVERAGE

1ltr., 5ltrs., 10ltrs., 20ltrs., 50ltrs.

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK - 1ST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



SHELFLIFE&STORAGE

DIMAPCHEMRR will have a shelf life of **24 months** in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C. Storage at higher temperature or high humidity may reduce shelf life.

HEALTH&SAFETY

It is recommended to use hand gloves while application of DIMAPCHEMRR .Avoid contact with eyes and skin

APPLICATION

In case of heavy rusting of steel reinforcement, M.S. Plates or any other M.S. Surface, remove the loose rust by wire brushing, chipping, hammering or grinding so that majority of rust scale is removed.

Apply **DIMAPCHEMRR** on affected surface by using cotton waste swab or by brush application. Leave the surface to react with **SAECORE RR** for at least 15 to 30 minutes. The rusty surface will change its color to original blackish steel then remove the loose rust particles by scrubbing or simple dusting with the brush.

TECHNICALINFORMATION

Non acidic and non alcoholic

The information given in this data sheet is based on both the current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept the responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being undertaken in our laboratories we advise customers in their-own interest to ensure that this data sheet has not been supersede by more up-to-date publication. All products are sold subjected to our standard conditionsof sale which are availablean request. Field services, where provided, does not constitute supervisory responsibility. For additional information,please contact our local DIMAPCHEM SARL – DIMAPCHEM

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM