



DIMAPCHEM- ZP Primer

SYNTHATIC ZINC PHOSPHATE PRIMER

BENEFITS

- Easy to apply with excellent rust inhibition.
- Very Quick Drying
- Can be over coated with , DIMAPCHEM- AKE QD, FD.
- Excellent weathering & chemical resistance properties
- Can be applied by brush, roller or airless spray..

DESCRIPTION

DIMAPCHEM- ZP Primer is single pack modified alkyd resin zinc primer, which can be applied on a steel or galvanized surface to protect the surface from weathering & chemical resistance.

PROPERTIES Color : Grey
Touch Drying : 2 - 5 minutes at 25°C

Hard Dry : 15 minutes **Over coating Intervals** : 20 minutes

Finish : Matt.
Flash Point : 32°C.
Volume Solids : 56% ± 2%
DFT : 40 - 50 microns
Number of Coats : One or Two

APPLICATION

Airless/tip: .018"/.020" pressure not less than 150 bar

Conventional / (pressure pot): 1.4mm Nozzle / 4 bars After thoroughly preparing steel surface, **DIMAPCHEM- ZP Primer** can be applied by brush, roller or airless spray on steel surfaces. Sandblasting is recommended for the proper performance of the product. **DIMAPCHEM- ZP Primer** can be over coated with our other range of protective systems.

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



PACKING & COVERAGE

1 Quart, U.S.Gallon, Pail and 200 Liters.

One liter of **DIMAPCHEM- ZP Primer** is sufficient to cover

11 M2 for a one or two coat application achieving total DFT of (50 microns theoretical)

QUALITY ASSURANCE

DIMAPCHEM SARL manufactures entire range of construction chemicals Protective coatings ,wood coatings ,decorative paints ,water proofing systems

TECHNICAL SERVICES

While new advances and changes will take place but one thing will never change is quality and meeting special needs of our customers. Our technical personnel & experts are available to provide additional information and technical assistance. We are eager to work with you in development of new product and resolve your problem.

SHELF LIFE & STORAGE

DIMAPCHEM- ZP Primer will have a shelf life of **12 months** in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C. Storage at higher temperature or high humidity may reduce shelf life.

QUALITY ASSURANCE

DIMAPCHEM SARL manufactures entire range of construction chemicals Protective coatings ,wood coatings ,decorative paints ,water proofing systems

the information given in this data sheet is based on both the current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept the responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being undertaken in our laboratories we advise customers in their-own interest to ensure that this data sheet has not been supersede by more up-to-date publication. All products are sold subjected to our standard conditionsof sale which are availablean request. Field services, where provided, does not constitute supervisory responsibility. For additional information,please contact our local DIMAPCHEM SARL – DIMAPCHEM-representative.

®Registered Trade Mark

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM