



DIMAPCHEM- ZRP

TWO PART, EPOXY ZINC RICH PRIMER

BENEFITS

- Easy to apply.
- Pre-weighed & premeasured
- Can be over coated with epoxy, polyurethane or chlorinated rubber etc.
- Excellent weathering & chemical resistance properties
- Can be applied by brush, roller or airless spray.
- Does not get affected by welding or cutting operation of steel.

QUALITY ASSURANCE

DIMAPCHEM SARL manufactures entire range of construction chemicals Protective coatings ,wood coatings ,decorative paints ,water proofing systems

TECHNICAL SERVICES

While new advances and changes will take place but one thing will never change is quality and meeting special needs of our customers. Our technical personnel & experts are available to provide additional information and technical assistance. We are eager to work with you in development of new product and resolve your problem.

Airless/tip: .018"/.020" pressure not less than 150 bar **Conventional / (pressure pot):** 1.4mm Nozzle / 4 bars
After thoroughly preparing steel surface, **DIMAPCHEM- ZRP** can be applied by brush, roller or airless spray on steel surfaces. Sandblasting is recommended for the proper performance of the product.

DIMAPCHEM- ZRP can be over coated with our other range of protective systems.

PACKING & COVERAGE

1 Quart, U.S.Gallon,U.S. Pail and 200 Liters.

One liter of **DIMAPCHEM- ZRP** is sufficient to cover 28 M2 for a one coat application achieving DFT of (20 microns theoretical)

RECOMMENDED SYSTEMS OVER VERL@ZRP: DIMAPCHEM EPE, EP MU ,EP MU HS, PU-D ,PU-UD

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



SHELF LIFE & STORAGE

DIMAPCHEM- ZRP will have a shelf life of **12 months** in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C. Storage at higher temperature or high humidity may reduce shelf life.

The information given in this data sheet is based on both the current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept the responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being undertaken in our laboratories we advise customers in their-own interest to ensure that this data sheet has not been supersede by more up-to-date publication. All products are sold subjected to our standard conditionsof sale which are availablean request. Field services, where provided, does not constitute supervisory responsibility. For additional information,please contact our local DIMAPCHEM SARL – DIMAPCHEM-representative.

®Registered Trade Mark

DIMAPCHEM

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM