



TM

DIMAPCHEM-EP G

SOLVENTED PROTECTIVE COATING

FOR STEEL SURFACES

BENEFITS

- Can be used steel, galvanized steel substrates & has excellent adhesion.
- Good protective properties.
- Excellent over coating characteristics.
- Available in different colors.
- Can be used for rebar - does not affect bonding of concrete with steel. § Chemical resistant.

PRODUCT

DIMAPCHEM-EP (G) is a two pack, solvent epoxy coating for, steel structures to provide protection from weathering abrasion and corrosion. It provides a durable coating suitable for application to both vertical & horizontal surfaces.

USES

DIMAPCHEM-EP (G) is used to protect steel surfaces and for enhanced resistance to oil, grease, abrasion and chemical attack.

PROPERTIES

Colors : Blue, Grey, Red, Green (Special colors on order)

Pot Life At 25°C : 7 hours,

Curing At 25°C : 1.5 hours

Touch Dry : 1 hours

Full Cure : 7 days

Temperature Range : During application, 5°C to 45°C

In Service : Max. 60°C, **DFT** : 175 micron/two coats.

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



APPLICATION

Surface Preparation: Steel Surfaces: Oil contaminated surfaces should be thoroughly cleaned with a degreaser and sand blasted. Where this is not possible, minimal surface preparation of wire brushing should be done. **DIMAPCHEM-EP (G)** can be applied directly to steel surfaces.

Priming: Normally primer is not required. But after grit blasting / sand blasting, if there is any delay to erection, one coat of **DIMAPCHEM-PRIMER** is advisable to prevent further flush rust.

Mixing: **DIMAPCHEM-EP (G)** is supplied as ready to use in pre-weighed packs of resin and hardener for easy on site mixing. Pour the hardener into the resin can, mix well using a paddle attached to an electric drill, for 2-3 minutes until a uniform color is obtained.

Application: DIMAPCHEM- EP (G) may be applied by

brush or airless spray to give a continuous coating on the prepared surface. A second coat may be subsequently applied when first coat is dried. Preferably next day.

Cleaning: Tools and mixers should be cleaned with **DIMAPCHEM-solvent** / Tool cleaner immediately after use.

PACKING & COVERAGE

DIMAPCHEM-EP (G) is supplied in One Quart, US. Gallon & Pail pack. Consist of Base and Hardener.

SHELF LIFE & STORAGE

DIMAPCHEM-EP (G) will have a shelf life of **12 months** in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C. Storage at higher temperature or high humidity may reduce shelf life.

HEALTH & SAFETY

Hand Gloves must be used. Goggles for overhead application to prevent contact with eye. Any splashes on skin should be washed with water and medical advice sought. In enclosed areas, good ventilation must be ensured, and smoking must be strictly prohibited while using **DIMAPCHEM-EP (G)**.

SPECIFICATION

DIMAPCHEM-EP (G) is a two pack, solvent, epoxy coating for steel structures to provide protection from weathering and abrasion. See below table for technical properties.

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



QUALITY ASSURANCE

DIMAPCHEM sarl manufactures entire range of construction chemicals protective coatings , wood coating, decorative paints, water proofing systems .

TECHNICAL SERVICES

While new advances and changes will take place but one thing will never change is quality and meeting special needs of our customers. Our technical personnel & experts are available to provide additional information and technical assistance. We are eager to work with you in development of new product and resolve your problem.

The information given in this data sheet is based on both the current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept the responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of the continuing research and development being undertaken in our laboratories we advise customers in their-own interest to ensure that this data sheet has not been supersede by more up-to-date publication. All products are sold subjected to our standard conditions of sale which are available on request. Field services, where provided, does not constitute supervisory responsibility. For additional information, please contact our local DIMAPCHEM SARL – DIMAPCHEM-representative. ®Registered Trade Mark

Technical Summary For DIMAPCHEM-EPG	
Chemistry	
<i>Color</i>	White, Grey & (Special colors on order)
<i>gloss level</i>	Semi Gloss
<i>Volume Solids</i>	45% ± 2%
<i>typical thickness</i>	50 Micron dry Equivalent to 95 Microns Wet.
<i>theoretical coverage</i>	10 M2 / Liter at 50 Microns
<i>practical coverage</i>	Allow Appropriate Loss Factor
<i>Flash Point</i>	27 °C
<i>Specific Gravity</i>	1.53 Kg/l
<i>Thinner to use</i>	DIMAPCHEM EP
<i>HARDENER</i>	EP HARDENER 20%
Application Method	
<i>common application fields</i>	General Steel

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



<i>Application methods</i>	Airless/tip: .018"/.020", pressure at tip not less than 150 bar Conventional / (pressure pot): 1.4mm Nozzle / 4 Bars Brush Roller
<i>Number of Coats</i>	One Coats
<i>Recoating interval at 25°C</i>	4 - 6 Hours / Max 7 Days
<i>Thinning cleaner</i>	DIMAPCHEM-Cleaning Thinner
<i>preparation of substrate</i>	For Iron SA 2.5
<i>Dry Time</i>	1 Hour Touch Dry, 3 - 5 Hours Hard
<i>Time to clean application equipment</i>	Immediately after use.
<i>Packaging</i>	1 Quart, U.S. Gallon & Pail
<i>storage</i>	Between 5°C and 45°C Degrees
<i>Shelve life storage</i>	12 Month
<i>Shipping weight not including pallets and boxes</i>	us gallon/---kg imp pail of gallon/---kg 5usg /---kg 25litrs----kg pail

recommended systems and compatibility

Top Coat DIMAPCHEM-EPE, MU
Top Coat DIMAPCHEM-PU - UD, SD, D

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK - 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM