



<b>Technical Summary For DIMAPCHEM VARNISH QD</b>	
<b>Chemistry</b>	
<i>Color</i>	CLEAR
<i>gloss level</i>	Matt, Semi Gloss and Gloss(25%-80%)
<i>Volume Solids</i>	40%+/-2%
<i>typical thickness</i>	50 Micron dry Equivalent to 125 Microns Wet.
<i>theoretical coverage</i>	10/12 M2 / Liter at 50 Microns
<i>practical coverage</i>	Allow Appropriate Loss Factor
<i>Flash Point</i>	> 32 °C
<i>Specific Gravity</i>	0.95Kg/l
<i>Thinner to use</i>	VERLASOL
<b>Application Method</b>	
<i>common application fields</i>	<b>General Steel, Wood</b>
<i>Application methods</i>	Airless/tip:0 .011"/0.013", pressure at tip not less than 120 bar Conventional / (pressure pot): 1.4mm Nozzle / 4 Bars Brush Roller
<i>Number of Coats</i>	1 OR 2
<i>recommended time interval between coats at 21°C</i>	Over Night
<i>Thinning</i>	20-30%
<i>cleaner</i>	DIMAPCHEM Cleaning Thinner
<i>preparation of substrate</i>	Sanding ,and staining if required for wood timber and veneer
<i>Dry Time</i>	
<i>Time to clean application equipment</i>	Immediately after use.

DEKWANEH-ROUND POINT  
AL HAYEK -38 CENTRE  
HAYEK – 1RST FLOOR  
+961 : 71-609609 7 -949396  
WWW.DIMAPCHEM.COM



<i>Packaging</i>	1 Quart, U.S. Gallon & US Pail
<i>storage</i>	Between 5°C and 45°C
<i>Shelve life storage</i>	12 Month
<i>Shipping weight not including pallets and boxes</i>	US GALLON 3.785LIT/- US PAIL 19LIT QUART

# DIMAPCHEM

DEKWANEH-ROUND POINT  
AL HAYEK -38 CENTRE  
HAYEK – 1RST FLOOR  
+961 : 71-609609 7 -949396  
WWW.DIMAPCHEM.COM