



DIMAPCHEM AKE varnish

ALKYD BASED VARNISH RESISTANCE
OUTDOOR PAINT FOR WOOD
SURFACES

BENEFITS:

- Ready to use can easily be applied by brush or roller
- Good and abrasion resistance
- Seals and dust proofs the surface
- Compatible with most substrate finishes
- Provides easily cleanable floor surfaces
- Internal and external use
- Resistant to ultra violet radiation
- Excellent adhesion to wood timbers veneer stain, surfaces

USES:

For Protective and Decorative purpose - Wood Surfaces, stained timbers and veneer ,boats, wooden garden furniture pergolas etc...

DESCRIPTION:

DIMAPCHEM AKE is a single pack, solvent, alkyd resin based clear paint. It forms a tough form that is highly resistant to UV and can be applied over oil base stain on veneer or wood timber .

PROPERTIES:

Gloss Level : 70 to 80 on tin plate at 20°C

gloss head

Drying Time At 25°C : Tack free - 3 hrs.

Hard dry – 4 to 6 hrs.

Re-coating Period : Overnight.

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



Chemical Resistance: Resistant to spillages of dilute minerals, Vegetable oils, etc.

APPLICATION:

Surface Preparation : (a) wood shall be sound and free from oil, grease, laitance and other contaminates. Previously applied paint must be removed. Sand well the surface with a 320 grid sanding paper followed by 120 grid to make smoother the wood substrate , and then start by diluting with mineral spirit and apply by roller or brush or spray.

PACKING & COVERAGE:

1 Quart, U.S. Gallon, Pail 19and 200 Liters, Coverage is very much dependent on the porosity of the substrate. Coverage will be 12 to 15 m² per kg per one coat.

SHELF LIFE & STORAGE:

DIMAPCHEM AKE will have a shelf life of **12 months** in unopened containers when kept in dry conditions at a temperature between 5°C to 45°C. Storage at higher temperature or high humidity may reduce shelf life.

LIMITATIONS:

DIMAPCHEM AKE should not be applied on a surface/ substrates that are subject to continues seepage or dampness.

Equipment Cleaning : Clean all equipment with **DIMAPCHEM TOOL CLEAN** or mineral spirit for brush and roller and xylene for spray gun and pumps immediately after use **DIMAPCHEM AKE varnish** .

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



HEALTH & SAFETY:

DIMAPCHEM AKE is a flammable material. Avoid exposure to naked flame or sources of ignition. For specific advice regarding any aspect of this product please consult our Technical Section. Technical properties

Gloss available 20% to 80%

Solvents mineral spirits ,turpentine

Solid ~ 35%

Drying time 24hrs

Touch dry 4hrs

Overcoat 3hrs

Stainable yes with oil base stain

Application brush-roller-pressure pot-
airless(0.011"nozzle-2000psi)

m²/liter 6/7m²/coat 50microns(without
loss factor)

application substrate wood & steel

typical solvent dilution for roller and brush pressure pot

30% for airless spray :15-20% number of coat 1 or 2

TECHNICAL SERVICES:

While new advances and changes will take place but one thing will never change is quality and meeting special needs of our customers. Our technical personnel & experts

are available to provide additional information and technical assistance. We are eager to work with you in development of new product and resolve your problem

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK - 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM



<i>Time to clean application equipment</i>	Immediately after use.
<i>Packaging</i>	1 Quart, U.S. Gallon & Pail
<i>storage</i>	Between 5°C and 45°C
<i>Shelve life storage</i>	12 Month
<i>Shipping weight not including pallets and boxes</i>	US GALLON 3.785LIT/- EURO GALLON 5LIT US PAIL 19LIT p EURO PAIL 25 LIT

DIMAPCHEM

DEKWANEH-ROUND POINT
AL HAYEK -38 CENTRE
HAYEK – 1RST FLOOR
+961 : 71-609609 7 -949396
WWW.DIMAPCHEM.COM